



VURA[®]
Time To Build Better

VURA **Polifill** L[™]

VURA Polifill-L is a water clear liquid, low viscous 2 component product based on UV-stabilized, unsaturated premium polyester resins. It is used for gluing and filling clear white marbles like Carrara and similar stones, also for filling the travertines and similar stones. Very stable to sunlight. It has a very low shrinkage. At low temperature, it has good reactivity.

CHARACTERISTICS

- Premium polyester base transparent liquid
- Low viscosity, therefore very good penetration
- No color of its own, therefore suited for light and white, mainly transparent-crystalline natural stones
- Fast setting and curing time
- Easily to apply and polish
- Good UV stability
- Very good adhesion on natural stone
- Bigger defects, corners and edges can be filled due to slow hardening and low tensions
- Resistant to water, petrol and mineral oils
- Grindable after hardening
- Colors can be mixed as per desired

APPLICATION AREAS

VURA Polifill-L is mainly used in stone processing industry for strengthening of larger areas of light or white, transparent- crystalline natural stones e.g. Thassos, Carrara, Onyx etc.. Due to its low viscosity, liquid and colourless-transparent appearance, bonding can be made which maintain the stereoscopic structure of the stone.

By adding little quantity of Polyester color paste a similar look like natural stone can be achieved. Granite, Marbles, Tiles, Sandstones, Cementitious tiles. Walls, floors, Tile on tile applications, Dry areas, worktops.

INSTRUCTIONS TO USE

SURFACE PREPARATION:

The surface to be treated must be clean, completely dry and roughened. It should be free of moisture, dirt, oil and grease etc.

Colouring is possible by adding Polyester colouring pastes up to max 5%.

APPLICATION METHOD:

Use gloves during application. Ensure proper and thorough mixing of resin (Part A) and hardener (Part B) before applying. The mixture can be worked for approx. 15-20 minutes (23° C). Do not allow excess material to dry on surface. After approx. 6-8 hours the treated parts can be exposed to strain, after 12 hours approx. they can be further processed (grinding, milling, drilling).

The hardening process is accelerated by heat and delayed by cold. Tools can be cleaned with thinner or mineral spirit.

SPECIAL NOTE

- Professional use only
- Use Gloves to protect your hands
- The products only harden with Hardener B liquid
- Hardener portions higher than 2% cause intensive discoloring
- Hardener portions less than 1% and low temperatures considerably delay hardening
- Permanent influence of heat (> 50° C) causes discoloring and reduces the bonding properties
- Non-durable resistance of bonding which are frequently exposed to humidity and frost
- The hardened **VURA Polifill-L** has a slight tendency to yellowing in outdoor application
- Only moderate adhesion on fresh, alkaline building materials (e.g. concrete, concrete bricks)
- Once hardened, the filler can no longer be removed by solvents. Removal is only possible mechanically or by higher temperature (> 200° C)
- For proper waste disposal the container must be completely empty
- Being worked properly, the hardened **VURA Polifill-L** is generally not injurious to health

Vura Bau-Chemie LLP

1302, 13th Floor,
Elite Business Hub, Sola,
Ahmedabad 380060,
Gujarat, India.

www.vura.ae

+91 79 4849 2890
care@vura.ae





VURA[®]
Time To Build Better

COVERAGE

10-20 m² / Litre (depending on the porosity of the marbles / stones)

TECHNICAL DATA

Color	:	Water Clear Transparent
Density	:	1.11-1.13 g/cm ³
Ratio of use	:	1 to 2 ml of hardener in 100ml of PoliFill-L
Gel time	:	20-25 minutes
Working time	:	
a) at 20° C	1% of hardener B	: 30-35 minutes
	1.5% of hardener B	: 20-25 minutes
	2% of hardener B	: 15-18 minutes
b) with	1.5 % of hardener	
	at 10° C	: 35-40 minutes
	at 20° C	: 20-25 minutes
	at 30° C	: 15-20 minutes
Tensile Strength	:	25-30 N/mm ²
Bending Strength	:	50-60 N/mm ²

PACK SIZE

1 L with 20 ml hardener dropper bottle.

SHELF LIFE

If stored in dry and cool condition in its closed original container at least 9 months from production. Keep away from source of heat, humidity and sun light.

HEALTH & SAFETY:

Please read Material Safety Data Sheet before handling or using this product.

IMPORTANT NOTICE:

The above information is based on the latest stage of development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trials of the product, in an inconspicuous area or fabrication of a sample piece.

This Datasheet is an information document drawn up in good faith. The information herein is based on tests carried out in our labs and is correct on the basis of our experience, but must be considered only as indicative because of the nature of the product whose behaviour varies with the minimal change in the surrounding conditions (environmental parameters, materials it comes into contact with, storage and ageing methods, etc.) For this reason, the information herein, even if based on our best knowledge, is no guarantee for the user since the customer's application, use and processing of our products and of the final product are beyond our control and are therefore wholly the customer's responsibility. We trust the tests we carried out can be a useful indication, even if we cannot accept any responsibility with regard to the result of your processing. It is the user's responsibility and duty to perform preliminary tests on the specific application, to assess suitability to the required use as it is his/her duty to check that the use of our products complies with the current laws, regulations, provisions and patents. This information must not be considered as an authorization and is no encouragement to infringe any patent. The data can be changed without notice and must not be considered as legally meaningful.

This technical data sheet supersedes all previous editions relevant to this product. Please be aware that this Technical Data Sheet only relates to a product manufactured in the specific relevant production site.

Vura Bau-Chemie LLP

1302, 13th Floor,
Elite Business Hub, Sola,
Ahmedabad 380060,
Gujarat, India.

www.vura.ae

+91 79 4849 2890
care@vura.ae

